

मानव निर्मित वस्त्र अनुसंधान संघ
(वस्त्र मंत्रालय, भारत सरकार से संलग्न)

टेक्स्टाइल मार्केट दूरभाष केन्द्र के समीप, रिंग रोड, सुरत-३९५ ००२.

दूरभाष : (+९१ २६१) २३२३२११, २३३७०६२

टेली-फैक्स : (+९१ २६१) २३२२५०० टेलीग्राम : "मंत्रा"

ई-मेल : director@mantrasurat.org वेबसाइट : www.mantrasurat.org

Registered under Bombay Public Trust Act 1950 & Societies Registration Act 1860, Linked to Ministry of Textiles, Govt. of India, New Delhi.

Laboratories MANTRA, Surat.

Format No: SC/Test Report/04/00

MAN MADE TEXTILES RESEARCH ASSOCIATION

(LINKED TO THE MINISTRY OF TEXTILES, GOVT. OF INDIA)

Near Textile Market Telephone Exchange, Ring Road, SURAT-395 002.

Phone :- (+91 261) 2323211, 2337062

Telefax :- (+91 261) 2322500, Telegram : 'MANTRA'

E-mail : director@mantrasurat.org Website : www.mantrasurat.org

SH-600

SAMPLE TESTING REPORT

Test Report No. : MANTRA/DTC/520

Recd. Dt. : 16/09/2019 13:14

Party / Company Name : SHRIJI MARKETING

Compl. Dt. : 18/09/2019 17:09

Address : VEGAM

Detail of Sample/s : ONE OIL SAMPLE/S SUBMITTED BY THE PARTY
MARKED AS - CALIBER-2000

Quantity/Samples : 1

(Vide Req No. MANTRA/DTC-520)

TEST RESULT

FLASH POINT (C.O.C) : 240 + 2 C

ASH CONTENT : NIL

KINEMATIC VISCOSITY AT 40 C : 300.15 CST

KINEMATIC VISCOSITY AT 100 C : 16.64 CST

EVAPORATION LOSS AT 200 C : 0.3 %

FOR 2 HOURS

SURAT

DATE 18/09/2019

Authorized by

Issued by

- NOTE (A) This report is for your private use only and should not be used for publicity or litigation.
- (B) Authenticity of this report could be validated with office copy at MANTRA.
- (C) The Submitted Sample/s was/were not drawn, Except Environment Audit by "MANTRA"
- (D) In case of complaints contact MANTRA within 30 days of issue of the report.
- (E) The test results relate only to the tested items.
- (F) This report shall not be reproduced, except in full, without the written approval of this Laboratory.